

824 Tittabawassee Rd, Saginaw, MI 48604

Ph: (989) 2491105 Fx: (989) 2491171

MECHANICAL GRAIN SIZE ANALYSIS

| Project Name: | Eggers - General Testing Services | Proj. No. | 13-069-007 |
|---------------|-----------------------------------|---------------|-------------|
| Location: | N Graham Rd | Tested by: | S MacDonald |
| Contractor: | N/A | Date: | 11/17/2023 |
| Arch./Eng.: | N/A | _Sample No.: | 1 |
| Supplier: | N/A | Intended Use: | |
| | | | |

Light Brown Sand

| Physical Data | | Intitial Weight of Sam | ole Weight Aft | Weight After Wash (200) | |
|---------------|---------------|------------------------|----------------|-------------------------|--------------------------------|
| | | 936.7 | 923.2 | | 1.4% Specified % Passing |
| Seive No. | Mass Retained | % Retained | % Cumulative | % Passing | |
| 2" | 0.0 | 0.0 | 0.0 | 100 | Class II |
| 1.5" | 0.0 | 0.0 | 0.0 | 100 | |
| 1" | 0.0 | 0.0 | 0.0 | 100 | 60-100 |
| 3/4" | 0.0 | 0.0 | 0.0 | 100 | |
| 1/2" | 0.0 | 0.0 | 0.0 | 100 | |
| 3/8" | 0.0 | 0.0 | 0.0 | 100 | |
| No. 4 | 0.0 | 0.0 | 0.0 | 100 | 50-100 |
| No. 8 | 0.0 | 0.0 | 0.0 | 100 | |
| No. 16 | 0.2 | 0.0 | 0.0 | 100 | |
| No. 30 | 3.8 | 0.4 | 0.4 | 100 | |
| No. 50 | 135.2 | 14.4 | 14.9 | 85 | |
| No. 100 | 584.2 | 62.4 | 77.2 | 23 | 0-30 |
| No. 200 | 196.0 | 20.9 | 98.2 | 1.8 | 0 to 7 |
| Pan | 3.8 | 0.4 | 98.6 | | |
| LBW | 13.5 | 1.4 | 100.0 | | |
| TOTAL | 936.7 | 100.0 | | | |

☑ complies with project specifications

□ does not comply with project specifications

Remarks:

Sampled By:

Sample Source

Eggers

Reported By: S. MacDonald